


EPOPLEX[®]



GLOMARC[®] 90 ***Viscosity vs. Temperature***

1000 East Park Avenue • Maple Shade, NJ 08052 • 856.667.8399 • FAX: 856.779.2963

GLOMARC 90 - Viscosity (cP)

Temperature	White Amine (Pigmented Side)	Yellow Amine (Pigmented Side)	Isocyanate
86°F/30°C	3,235	3,060	1,443
104°F/40°C	1,560	1,720	660
122°F/50°C	865	1,270	471
140°F/60°C	465	1,110	223