



GLOMARC 50 - Viscosity (cP)

Temperature	Hardener	White	Yellow
70°F/21°C	43,000	46,000	48,000
75°F/24°C	24,000	29,000	29,000
80°F/27°C	8,000	4,700	3,250
85°F/29°C	6,360	4,250	2,890
90°F/32°C	4,840	2,680	2,340
95°F/35°C	3,040	2,100	2,060
100°F/38°C	2,260	1,840	1,800
105°F/41°C	1,680	1,390	1,280
110°F/43°C	1,290	1,070	1,040
115°F/46°C	1,040	980	880
120°F/49°C	860	850	665
125°F/52°C	670	630	560
130°F/54°C	570	290	390