

PRODUCT DESCRIPTION

Stonres RTZ is a nominal 5 mm resilient urethane flooring system. This easy to clean, seamless, resilient system provides exceptional acoustic efficiency and ergonomic comfort. The system combines superior aesthetics with the excellent wear and stain resistance offering progressive design options. It is comprised of:

Note: This product is highly recommended for healthcare environments.

Stonres RTZ Mortar

A three-component, UV resistant, resilient urethane mortar consisting of urethane resin, curing agent and coarse aggregate

Stonres Groutcoat

A two-component, clear, UV resistant, aliphatic, polyaspartic urethane grout coat

Stonseal CF7

Stonseal CF7 is a two-component, clear flat, high performance, water-based, VOC compliant, polyurethane coating

PACKAGING

Stonres RTZ is packaged in units for easy handling. Each unit consists of:

Stonres RTZ Mortar

12 cartons, each containing:
 1 foil bag of Isocyanate
 (12) 5 gallon pails of Polyol

12 bags of aggregate

Stonres Groutcoat

0.5 carton containing:
 1 poly bag of Isocyanate
 (1) 1 gallon can of Amine

Stonseal CF7

1 carton containing:
 1 foil bag of Isocyanate
 (1) 1 gallon pail of Polyol

COVERAGE

Each unit of Stonres RTZ will cover approximately 20.4 m² of surface at the nominal 5 mm finished thickness.

STORAGE CONDITIONS

Store all components of Stonres RTZ between 18 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life of the Mortar is 3 years, all other components have a shelf life of one year in the original unopened containers.

COLOR

Stonres RTZ is available in 8 standard colors and an extensive color palette. Refer to the Stonres RTZ color sheet. Custom colors are available upon request.

SUBSTRATE

Stonres RTZ is suitable for application over properly prepared concrete, wood or steel surfaces. It is not recommended for use over asphalt, mastic, gypsum-based products, brick or painted surfaces. These must first be removed by mechanical means to expose the substrate prior to overlayment.

PHYSICAL CHARACTERISTICS

Tensile strength (ASTM C-307)	8 N/mm ²
Hardness (ASTM D-2440, Shore A)	85
Percent Elongation (ASTM D-638)	150%
Impact Resistance (ASTM D-2794)	> 7 Nm
Static load limit (ASTM F-970)	0.05 mm (57 kg load)
Resistance to heat (ASTM F-1514)	Delta E <8 (7 days@70°C)
Residual indentation (ASTM F-1914)	<1% thickness (64 kg load)
Abrasion Resistance (ASTM D-4060, CS-17)	0.03 gm
Thermal Coefficient Of Linear Expansion (ASTM C-531)	5,94 x 10 ⁻⁵ mm/m°C
Flammability (ASTM E-648)	Class I
Noise Reduciton Coefficient (ASTM C-423)	0.05
VOC Content (ASTM D-2369)	RTZ mortar - 10 g/l Stonres Groutcoat - 90 g/l Stonseal CF7 – 47 g/l (method C)
Cure Rate (@77°F/25°C)	12 hours for Foot traffic 48 hours for normal operations

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard's representative or Technical Service.

Note: A flat level substrate is required for Stonres RTZ application and cannot be installed over a pitched surface.

PRIMING

The use of the Standard Primer/SL Primer priming system is required for all applications of RTZ over concrete or wood. Metal substrates must be primed immediately following preparation with HT primer. The substrate must be free of voids and pinholes after priming and prior to the start of the Mortar application and the primer layer must not be cured for longer than 24 hours to ensure proper inter-coat adhesion.

MIXING

- Proper mixing is critical for the products to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing is required for all components.
- See Stonres RTZ Directions for further details

APPLYING

- DO NOT attempt to install material if the temperature of the Stonres RTZ components and substrate are not within 18 to 30°C. **The cure time and application properties of the material are severely affected if the temperatures are outside of this range.**
- Stonres RTZ Mortar material is mixed just prior to use in accordance with prescribed directions. The base material is then screed rake applied and spike rolled to finish.
- After a minimum of 20 hours curing time, sand the surface of the RTZ Mortar using the recommended grit sandpapers.
- Squeegee apply and backroll Stonres Groutcoat with a medium nap roller.
- After 4 hours of minimum cure time, roller apply the Stonseal CF7. After 12 hours of cure, apply a second coat of Stonseal CF7. Allow a minimum of 12 hours of cure before foot traffic and 48 hours before washdown/cleaning procedures commence.

Note: Two coats of Stonseal CF7 are required for all applications of Stonres RTZ.


- Detailed application instructions can be found in the Stonres RTZ Directions.

NOTES

- Procedures for cleaning of the flooring system during Operations can be found in the Stonhard Floor Maintenance Guide.
- Specific information regarding chemical resistance is available in the Stonres Chemical Resistance Guide.
- Material Safety Data Sheets for Stonres RTZ are available online at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.
- Requests for technical service or literature can be made through local sales representatives and offices or corporate offices located worldwide.

CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials - Properties and requirements“ specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as **per Annex ZA., Table ZA.1.5 and 3.3** and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011

	
StonCor Europe Rue du Travail 9 1400 Nivelles, Belgium	
13	
EC-DOP-2013.03.004	
EN 13813 SR-AR1.0-B2.0-IR7	
Synthetic resin flooring system for use internally in buildings (system as per Product Data Sheet)	
Release of corrosive substances:	SR
Wear resistance:	AR1.0
Adhesion strength by pull-off test:	> B2.0
Impact resistance:	IR 7
Sound insulation:	▲Lw 6dB
Chemical resistance:	CRG*
* CRG: see Stonhard Chemical Resistance Guide	

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

STONHARD A Division of **StonCOR**^{Group}

www.stoncor-europe.com

Belgium	+32.67493710	Spain/Portugal	+35.1707200088	Germany	+49.240541740
France	+33.160064419	United Kingdom	+44.1256336600	The Netherlands	+31.165585200
Poland	+48.422112768	East Europe	+31.165585200	Italy	+39.02253751