

PRODUCT DESCRIPTION

Stonseal UT7 is a two-component, solvent-free, abrasion-resistant, pigmented urethane sealer. It is formulated to increase abrasion and chemical resistance while improving cleanability. Stonseal UT7 is easily applied and hardens to an attractive gloss finish.

USES, APPLICATIONS

Stonseal UT7 is a high-gloss sealer designed for use whenever a high-gloss, abrasion-resistant, smooth finish is required. It may be applied on various substrates to both vertical and horizontal surfaces. Some applications of Stonseal UT7 are:

- In conjunction with various Stonhard flooring systems
- For substrates requiring a protective sealer that is easily cleaned and maintained

PRODUCT ADVANTAGES

- Long-term abrasion and chemical resistance
- Excellent bond strength assures good adhesion
- Protects against moisture penetration
- Durable, gloss finish permits easy cleaning and maintenance
- Factory proportioned packaging ensures consistent, high quality, simplified mixing

PACKAGING

Stonseal UT7 is packaged in units for easy handling. Each unit consists of:

- 1 carton containing:
 - 4 foil bags of Isocyanate
 - 4 poly bags of Polyol

COVERAGE

Approximately 17.6 m² per unit over a textured substrate like Stonclad UT. Approximately 37 m² for one coat and 18.5 m² for two coats over an unsealed mortar like Stonclad UR.

Note: It is recommended to use two coats over Stonclad UR due to outgassing of the mortar.

STORAGE CONDITIONS

Store all components of Stonseal UT7 between 16°C and 29°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 2 years in the original, unopened container.

CHEMICAL RESISTANCE

Refer to the Stonclad Chemical Resistance Guide for the most up-to-date information.

SURFACE PREPARATION

Before coating a smooth floor like Stonclad UR, all trowel marks and surface imperfections must be removed to produce a smooth surface. Grind the floor using a floor grinder with medium stones and vacuum using an industrial wet/dry vacuum to remove all dust particles. Before coating a textured floor like Stonclad UT, the floor must be swept and vacuumed to remove all extra/loose aggregate. The Stonhard floor is now ready to be coated with Stonseal UT7.

PHYSICAL CHARACTERISTICS

Pot Life (@ 21°C)	20 minutes
Cure Rate (@ 25°C)	6 hours for tack-free surface 24 hours minimum for normal operations
Abrasion Resistance (ASTM D-4060, CS-17)	0.03 gm max. weight loss
VOC Content (ASTM D-2369, Method E)	20 g/l

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

MIXING

Stonseal UT7 is supplied in factory proportioned quantities. To achieve thorough and proper mixing, the Stonseal UT7 must be mechanically mixed using a heavy-duty, slow-speed drill (400 to 600 rpm) with a mixing blade. Empty the contents of the polyol and isocyanate into a clean mixing container. Using a mixing blade, mix the material for 2 minutes. Avoid high speed mixing that will entrain air into the mix. Thorough mixing of the two components is required.

POT LIFE

After mixing, Stonseal UT7 has a working time of approximately 20 minutes at 21°C. The working time may vary depending upon ambient and surface conditions.

APPLYING

Stonseal UT7 can be applied at ambient temperatures of 16 to 29°C. The Sealer must be applied immediately after mixing the two components. Over a smooth surface, Stonseal UT7 is applied with a squeegee and then backrolled with a medium nap roller to remove squeegee lines. A brush may be used when necessary. For applications over a Stonclad UT system, Stonseal UT7 must be dip and rolled using a medium nap roller to ensure proper coverage is obtained and the sealer is not applied too heavy. Additional coats may be applied when the surface is tack-free (about 6 hours). Any questions regarding the application of Stonseal UT7 should be directed to Stonhard's Technical Service Department.

CURING

The surface of Stonseal UT7 will be tack-free in 6 hours at 25°C. The coated area may be put back into service in 24 hours. Ultimate physical characteristics will be achieved in 7 days.

RECOMMENDATIONS

- Apply only on a clean, sound and properly prepared substrate.
- Minimum ambient and surface temperatures are 16°C at the time of application.
- Do not use water or steam in the vicinity of the application.
Moisture can seriously affect the working time and properties of the material.
- Application and curing times are dependent upon ambient and surface conditions.

PRECAUTIONS


- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses and impermeable gloves are required.
- In case of contact, flush the area with copious amounts of water for 15 minutes and seek medical attention. Wash skin with soap and water.
- Use only with adequate ventilation.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonklean Floor Cleaning Procedures Brochure.
- For environments not referenced in the Chemical Resistance Guide, consult Stonhard's Technical Service Department for recommendations.
- Safety Data Sheets for Stonseal UT7 are available online at www.stoncor-europe.com under Products or upon request.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard's products.
- Requests for technical literature or service can be made through local sales representatives or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials - Properties and requirements“ specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as per Annex ZA., Table ZA.1.5 and 3.2 and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011



StonCor Europe
Rue du Travail 9
1400 Nivelles, Belgium

08

DOP-2013.13.006

EN 13813 SR-AR0.5-B2.0

Synthetic resin coating system for use internally in buildings²
(system as per Product Data Sheet)

Reaction to fire:	B _{fl} -S ¹
Release of corrosive substances:	SR
Wear resistance:	≤ AR0.5
Adhesion strength by pull-off test:	> B2.0
Chemical resistance:	CRG ²

(1) CRG: see Stonhard Chemical Resistance Guide
(2) Tested as part of a system build-up with Stonclad GS

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev 07/18
© 2018 Stonhard



STONHARD
www.stoncor-europe.com



European Offices:

Belgium +32 674 93 710
France +33 160 064 419
Poland +48 422 112 768

Spain/Portugal +351 707 200 088
United Kingdom +44 125 63 36 600
East Europe +48 422 112 768

Germany +49 240 541 740
The Netherlands +31 165 585 200
Italy +39 022 53 751