

PRODUCT DESCRIPTION

Stonchem 556 is a 100% solids, high performance, epoxy hybrid lining system applied at a nominal 1.5 mm. The resin, engineering fabric, mortarcoat, mineral composite topcoat sequencing provides a smooth, heavy-duty chemical barrier which is resistant to small static cracks and moderate thermal shock. The Stonchem 556 system has excellent resistance to caustics and moderate concentrations of acids. This system contains no harmful volatiles to contaminate food present in an area.

USES, APPLICATIONS

- Secondary containment areas
- Concrete sumps, vaults and trenches
- Pump pads and pedestals
- Storage tanks
- Neutralization pits

PRODUCT ADVANTAGES

- Excellent chemical resistance to caustics and moderate concentrations of acids
- Engineering fabric aids in crack resistance
- Mortarcoat for added abrasion resistance
- Mineral composite topcoat for increased impermeability
- Factory proportioned units for easy application

CHEMICAL RESISTANCE

Stonchem 556 is formulated to resist a variety of chemical solutions. (Refer to the Stonchem 500 Series Chemical Resistance Guide for lists of reagent concentrations and temperature recommendations.)

PACKAGING

Stonchem 556 is packaged in units for easy handling. A unit of Stonchem 556 consists of:

Saturant

1.2 cartons of Stonchem 500 Series Saturant
A carton contains:

- 6 foil bags of amine
- 6 poly bags of resin

Engineering Fabric

1 roll of Engineering Fabric
18.58 m² roll

PHYSICAL CHARACTERISTICS

| | |
|---|---|
| Tensile Strength (ASTM D-638) | 43 N/mm ² |
| Flexural Strength (ASTM C-580) | 83 N/mm ² |
| Flexural Modulus of Elasticity (ASTM C-580) | 6.9 x 10 ³ N/mm ² |
| Hardness (ASTM D-2240, Shore D) (100% concrete failure) | 85 to 90 |
| Abrasion Resistance (ASTM D-4060, CS-17) | 0.07 gm max. weight loss |
| Thermal Coefficient of Linear Expansion (ASTM C-531) | 2.16 x 10 ⁻⁵ m/mm°C |
| Color | Gray |

Note:The above physical properties were measured in accordance with the referenced standards. Samples of the actual system, including binder and filler, were used as test specimens.

Mortarcoat

0.5 carton of Stonchem 500 Series Mortarcoat
A carton contains:
6 foil bags of amine
6 poly bags of resin
3 bags of Mortarcoat aggregate

Topcoat

1 carton of Stonchem 500 Series Topcoat
A carton contains:
4 foil bags of amine
4 poly bags of resin

COVERAGE

Each unit of Stonchem 556 will cover approximately 16.72 m² at an application thickness of 1.5 mm.

STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils, fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent and rinsing with clean water. The surface must show open pores throughout and have a sandpaper texture. For recommendations or additional information regarding substrate preparation, contact Stonhard's Technical Service Department.

APPLICATION GUIDELINES

Before mixing and applying any material, make sure environmental conditions are satisfactory for application. For optimal working conditions, substrate temperature must be between 15 to 27°C. Measure the surface temperature with a surface thermometer. Cold areas must be heated until the slab temperature is above 12.7°C. This will allow the material to achieve a proper cure. Also, a cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a hot substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling.

APPLYING

Priming

Vacuum the substrate before priming and make sure the surface is dry. The use of HT Primer is necessary in all applications of Stonchem 556. This ensures maximum product performance. (See the HT Primer product sheet for details.)

Note: HT Primer must be tack-free prior to application of the Saturant – Base Coat. Saturant – Base Coat

Mix amine and resin in a 5 gallon bucket using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Pour the saturant onto the substrate and spread out with a 15 mil notched squeegee. The saturant should be spread out in a sequence to allow application of the engineering fabric. Do not leave any puddling during this squeegee step. Puddling will lead to over saturation of the engineering fabric.

Engineering Fabric

Place the engineering fabric on the saturant immediately after the saturant is applied. This is important to achieve maximum wetting. Press the engineering fabric into the saturant with a dry, medium nap roller. Overlap adjacent fabric 13 mm. Immediately apply the next saturant step.

Saturant

Mix amine and resin in a 5 gallon bucket using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Apply the saturant to the engineering fabric with a saturated medium nap roller. To wet the roller, dip it into the mixing bucket. Always work from the bucket. Do not pour the saturant directly onto the engineering fabric. This will decrease the saturant's coverage. If air temperature is above 27°C, the use of plastic buckets will increase the pot life of the material. The engineering fabric is completely saturated when white strands are no longer present. When the engineering fabric is completely saturated, roll with a ribbed roller to release air pockets in the reinforcement and to help mesh engineering fabric and saturant together. To saturate the overlaps, roll several times over the length of the overlap with a saturated roller. Then, roll with a ribbed roller several times until the overlap is no longer visible. Allow the saturant and engineering fabric to cure (usually 4 to 6 hours) before proceeding.

Mortarcoat

Lightly sand the engineering fabric and saturant layer with a sanding disc attachment in areas with protruding fibers. Pre-mix amine and resin in a 5 gallon mixing bucket with a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Next, gradually add mortarcoat aggregate while mixing for an additional 2 minutes. For vertical applications, use Vertical Mortarcoat aggregate. Mixing is complete when no dry clumps of material exist. Pour the material onto the floor and spread out with a 15 mil notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines. The material may appear rough at first but will level out to a smooth finish. For vertical surfaces, use a large steel trowel or knife to pull an initial coat of vertical material onto the wall, then finish smooth with a flat rubber squeegee.

Topcoat

Lightly sand the mortarcoat in areas where protrusions exist. Vacuum the area completely. Mix amine and resin in a 5 gallon mixing container using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for 2 minutes. Pour the material onto the floor and spread out with a 15 mil notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines, using long roll strokes to decrease the visibility of roller lines. For vertical surfaces, pour a bead of material along the base of the wall and, using a medium nap roller, roll the material onto the vertical surface. The wet film thickness of the coating is 250 to 300 microns. Check the thickness with a wet film gauge.

CURING

The surface of Stonchem 556 will be tack-free in 4 to 6 hours at 21°C. The coated area may be put back in service in 24 hours at 21°C. Ultimate physical characteristics will be achieved in 7 days.

RECOMMENDATIONS

- Apply only on clean, sound, dry and properly prepared substrates.
- Minimum ambient and surface temperature is 13°C at the time of application.
- Maximum surface temperature should not exceed 32°C during application. Substrate temperatures above 38°C will drastically affect the working time of the product.
- Substrate temperature should be greater than 3°C above dew point.
- Material should not be applied if humidity is above 85%.
- Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

PRECAUTIONS

- Toluene or Xylene solvents are recommended for clean up of Stonchem 556 material spills. Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The use of NIOSH/MSHA approved respirators using an organic vapor/acid gas cartridge is recommended.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles and impermeable gloves are highly recommended.
- In case of contact, flush the area with copious amounts of water for 15 minutes and seek medical attention. Wash skin with soap and water.
- Use only with adequate ventilation.

NOTES

- Material Safety Data Sheets for Stonchem 556 are available upon request.
- Specific information regarding chemical resistance of Stonchem 556 is available in the Stonchem 500 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

STONHARD A Division of **STONCOR** Group

www.stoncor-europe.com

| | | | | | |
|---------|---------------|----------------|----------------|-----------------|---------------|
| Belgium | +32 67493710 | Spain/Portugal | +351 707200088 | Germany | +49 240541740 |
| France | +33 160064419 | United Kingdom | +44 1256336600 | The Netherlands | +31 165585200 |
| Poland | +48 422112768 | East Europe | +31 165585200 | Italy | +39 02253751 |