

### PRODUCT DESCRIPTION

Stonchem 602 is a highly cross-linked, novolac epoxy lining system applied at a nominal thickness of 1 mm. The mortarcoat, mineral composite topcoat sequencing provides a light-duty chemical barrier for areas with occasional foot traffic. The Stonchem 602 has excellent resistance to concentrated sulfuric acid, chlorinated solvents and caustics.

### USES, APPLICATIONS

- Secondary containment areas
- Concrete pads and pedestals
- Process piping and equipment
- Storage tanks
- Neutralization pits
- Splash/spill areas

### PRODUCT ADVANTAGES

- Excellent chemical resistance to concentrated sulfuric acid, chlorinated solvents and caustics
- Mineral composite filled for increased impermeability
- Factory proportioned units for easy application

### CHEMICAL RESISTANCE

Stonchem 602 is formulated to resist a variety of chemical solutions. Please refer to the Stonchem 600 Series Chemical Resistance Guide for lists of reagent concentrations and temperature recommendations.

### PACKAGING

Stonchem 602 is packaged in units for easy handling. Each unit consists of:

#### Mortarcoat

0.5 cartons of Stonchem 600 Series Mortarcoat

A carton contains:

- 6 foil bags of amine
- 6 poly bags of resin
- 3 bags of Mortar aggregate

#### Topcoat

1 carton of Stonchem 600 Series Topcoat

A carton contains:

- 4 foil bags of amine
- 4 poly bags of resin

### COVERAGE

Each unit of Stonchem 602 will cover approximately 16.72 m<sup>2</sup> at a thickness of 1 mm.

### PHYSICAL CHARACTERISTICS

Tensile Strength (ASTM D-638)	30 N/mm <sup>2</sup>
Flexural Strength (ASTM C-580)	69 N/mm <sup>2</sup>
Flexural Modulus of Elasticity (ASTM C-580)	6.9 x 10 <sup>3</sup> N/mm <sup>2</sup>
Hardness (ASTM D-2240, Shore D)	85 to 90
Abrasion Resistance (ASTM D-4060, CS-17)	0.07 gm max. weight loss
Thermal Coefficient of Linear Expansion (ASTM C-531)	2.2 x 10 <sup>-5</sup> m/mm°C
Color	Gray

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual system, including binder and filler, were used as test specimens.

### STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. When stored in the unopened containers at the proper temperatures, the shelf life is 3 years.

### SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils, fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent and rinsing with clean water. The surface must show open pores throughout and have a sandpaper texture. For recommendations or additional information regarding substrate preparation, contact Stonhard's Technical Service Department.

### APPLICATION GUIDELINES

Before mixing and applying any material, make sure environmental conditions are satisfactory for application. For optimal working conditions, the substrate temperature must be between 15 to 27°C. Measure the surface temperature with a surface thermometer. Cold areas must be heated until the slab temperature is above 13°C. This will allow the material to achieve a proper cure. Also, a cold substrate will make the

material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling.

## APPLYING

### Priming

Vacuum the surface before priming and make sure the concrete substrate is dry. The use of HT Primer is necessary in all applications of Stonchem 602. This ensures maximum product performance. (See the HT Primer product data sheet for details.)

**Note:** HT Primer must be tack-free prior to application of the Mortarcoat.

### Mortarcoat

After the primer has been applied and allowed to fully cure, pre-mix the amine and resin in a 5 gallon mixing bucket with a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy mixer attachment for one minute. Next, gradually add Mortarcoat aggregate while mixing for an additional 2 minutes. For vertical applications, use Vertical Mortarcoat aggregate. Mixing is complete when no dry clumps of material exist. Pour the material onto the floor and spread out with a 15 mil notched squeegee. Backroll the material with a medium nap roller to remove squeegee lines. The material may appear rough at first but will level out to a smooth finish. For vertical surfaces, use a large steel trowel or knife to pull an initial coat of vertical material onto the wall, then finish smooth with a flat rubber squeegee.

### Topcoat

Lightly sand the Mortarcoat in areas where protrusions exist. Vacuum the area completely. Mix amine and resin in a 5 gallon mixing container using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for 2 minutes. Pour the material onto the floor and spread out with a 15 mil notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines, using long roll strokes to decrease the visibility of roller lines. For vertical surfaces, pour a bead of material along the base of the wall, and using a medium nap roller, roll the material onto the vertical surface. The wet film thickness of the coating is 250 to 300 microns. Check the thickness with a wet film gauge.

## CURING

The surface of Stonchem 602 will be tack-free in 4 to 6 hours at 21°C. The coated area may be put back in service in 24 hours at 21°C. Ultimate physical characteristics will be achieved in 7 days.

## RECOMMENDATIONS

- Apply only on clean, sound, dry and properly prepared substrates.
- Minimum ambient and surface temperature is 10°C at the time of application.
- Maximum surface temperature should not exceed 32°C during time of application.
- Substrate temperature should be greater than 3°C above dew point.
- Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within the recommended guidelines.

## PRECAUTIONS

- Avoid contact with Stonchem 602 resin and amine as they may cause skin, respiratory and eye irritation.
- The use of NIOSH/MSHA approved respirators using an organic vapor acid gas cartridge is recommended.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles and impermeable nitrile gloves are highly recommended.
- In the event of accidental eye contact, rinse eyes immediately with water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**
- Use only with adequate ventilation. Inhalation of vapors may cause severe headaches, nausea and possibly unconsciousness.

## NOTES

- Material Safety Data Sheets for Stonchem 602 are available upon request.
- Specific information regarding chemical resistance of Stonchem 602 is available in the Stonchem 600 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or to service can be made through local sales representatives and offices, or corporate offices located worldwide.

**IMPORTANT:**

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.



[www.stoncor-europe.com](http://www.stoncor-europe.com)

Belgium	+32 67493710	Spain/Portugal	+351 707200088	Germany	+49 240541740
France	+33 160064419	United Kingdom	+44 1256336600	The Netherlands	+31 165585200
Poland	+48 422112768	East Europe	+31 165585200	Italy	+39 02253751