

### PRODUCT DESCRIPTION

Stonchem 821 is a spark-proof vinyl ester lining system applied at a nominal thickness of 625 microns. The Stonchem 821 system has excellent resistance to a broad base of chemicals, including hydrofluoric acid, strong organic acids, caustics, solvents and moderate to strong inorganic acids.

### USES, APPLICATIONS

- Secondary Containment Areas/Tank Farms
- Concrete Sumps, Vaults and Trenches
- Pump Pads and Pedestals
- Chemical Storage Rooms

### PRODUCT ADVANTAGES

- Excellent chemical resistance to hydrofluoric acid
- Carbon filled
- Factory proportioned units for easy application

### CHEMICAL RESISTANCE

Stonchem 821 is formulated to resist a variety of chemical solutions. Please refer to the Stonchem 800 Series Chemical Resistance Guide which lists reagent concentration and temperature recommendations for each product.

### PACKAGING

Stonchem 821 is packaged in units for easy handling. Each unit consists of:

#### Topcoat

- 2 cartons of Stonchem 820 Series Topcoat
- A carton contains:
  - 2 jars of peroxide
  - 2 cans of resin

### COVERAGE

Each unit of Stonchem 821 will cover approximately 16.72 m<sup>2</sup> at a thickness of 625 microns.

### STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze. The shelf life is 6 months in the original, unopened container.

### PHYSICAL CHARACTERISTICS

Tensile Strength (ASTM D-638)	17 N/mm <sup>2</sup>
Flexural Strength (ASTM C-580)	48 N/mm <sup>2</sup>
Flexural Modulus of Elasticity (ASTM C-580)	3.4 x 10 <sup>3</sup> N/mm <sup>2</sup>
Hardness (ASTM D-2240, Shore D)	85 to 90
Abrasion Resistance (ASTM D-4060, CS-17)	0.10 gm max. weight loss
Thermal Coefficient of Linear Expansion (ASTM C-531)	3.6 x 10 <sup>-5</sup> mm/m°C
Color	Black
VOC (ASTM D-2369, Method E)	820 Topcoat 48 g/l

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

### SUBSTRATE

Stonchem 821, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

### SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service

## APPLICATION GUIDELINES

For optimal working conditions, substrate temperature must be between 15 to 27°C. Cold areas must be heated until the slab temperature is above 13°C to ensure the material achieves a proper cure. A cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling. Substrate temperature should be greater than 3°C above dew point. Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

## FIELD GEL TESTS

Due to the unique nature of the 800 Series resins, their reactivity is affected by storage conditions and age; therefore, it is important to test the cure of the materials prior to application. Gel tests should be performed for each lot of each product shipped to a job to prevent problems related to material curing. Field gel test kits are included in every shipment of 800 Series material. One gel test contains directions and all of the necessary materials to conduct the testing. Test all lots of material prior to use

## PRIMING

Vacuum the surface before priming, and make sure the concrete substrate is dry. The use of Stonchem 700/800 Series Primer is necessary in all applications of Stonchem 822. This ensures maximum product performance. (See the Stonchem 700/800 Series Primer Product Data sheet for details.)

**Note:** Stonchem 700/800 Series Primer must be tack-free prior to application of the Basecoat.

## APPLYING

### Basecoat

Mix the peroxide and resin in a 5 gallon mixing container, using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Pour the material onto the floor and spread out with a 15 mil notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines using long roll strokes to decrease the visibility of roller lines. For vertical surfaces, pour a bead of material along the base of the wall. Using a medium nap roller, roll the material up onto the wall. The wet film thickness of the coating is 250 to 300 microns. Check the thickness with a wet film gauge.

### Topcoat

Apply the same as the Basecoat.

**Note:** Stonchem 821 is not a conductive system and will not yield point to point readings.

## CURING

The surface of Stonchem 821 will be tack-free in 4 to 6 hours at 21°C. The coated area may be put back in service in 24 hours at 21°C. Ultimate physical characteristics will be achieved in 7 days.

## PRECAUTIONS

- Avoid contact with Stonchem 821 resin (vinyl ester resin and styrene monomer) and peroxide (catalyst/organic peroxide), as they may cause skin, respiratory and eye irritation.
- Acetone is recommended for clean up of Stonchem 821 resin (vinyl ester resin and styrene monomer) and peroxide (catalyst/organic peroxide) material spills. Use these materials only in strict accordance with the manufacturers' recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- **The use of NIOSH/MSHA approved respirators using an organic vapor/acid gas cartridge is mandatory.**
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses and impermeable gloves are required.
- In case of contact, flush area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**
- Use only with adequate ventilation. Inhalation of vapors may cause severe headaches, nausea and possibly unconsciousness.

## NOTES

- Material Safety Data Sheets for Stonchem 821 are available on line at [www.stonhard.com](http://www.stonhard.com) under Tech Info or upon request.
- Specific information regarding the chemical resistance of Stonchem 821 is available in the Stonchem 800 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices or corporate offices located worldwide

**IMPORTANT:**

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.



[www.stoncor-europe.com](http://www.stoncor-europe.com)

Belgium	+32 67493710	Spain/Portugal	+351 707200088	Germany	+49 240541740
France	+33 160064419	United Kingdom	+44 1256336600	The Netherlands	+31 165585200
Poland	+48 422112768	East Europe	+31 165585200	Italy	+39 02253751